




Glastherm® Grade HT220

- High Hot Compressive Strength
- Low Thermal Conductivity
- Oil and Moisture Resistant
- Reduces Heat Loss
- Helps Control Temperature
- Faster Mold Startup
- Rugged and Durable

Glastherm Grade HT220 is a thermal insulation sheet that is a highly heat-resistant material that combines low thermal conductivity with very high compressive strength at molding temperature. Finished to a close thickness tolerance, it is ideal for many of the more difficult molding applications.





Glastherm® Grade HT220

	Procedure	English Units	Typical Values	Metric Units	Typical Values
General Information					
Part Number					
Standard Color			Light Beige		Light Beige
Maximum Service Temp.		°F	608	°C	350
Continuous Use Temp.		°F	450	°C	220
Mechanical Properties					
Flexural Strength	ASTM D790	Psi	52,200	Mpa	360
Compressive Strength					
@68°F / 20°C	ASTM D695	Psi	72,500	Mpa	500
@302°F / 150°C	ASTM D695	Psi	55,100	Mpa	380
@392°F / 200°C	ASTM D695	Psi	40,600	Mpa	280
@550°F / 288°C	ASTM D695	Psi	35,000	Mpa	250
Compressive Modulus	ASTM D695	Psi	2,610,000	Mpa	18,000
Physical Properties					
Water Absorption	ASTM D570	% by wt.	0.2	% by wt.	0.2
Specific Gravity	ASTM D792	lbs/ft ³	1.85	g/cm ³	1.85
Thickness Tolerance		inches	±0.004	mm	±0.10
Coefficient of Thermal Expansion					
Across Thickness	ASTM D696	In/In/°Cx10 ⁻⁵	5.7	10 ⁻⁶ /K	5.7
Across Surface	ASTM D696	In/In/°Cx10 ⁻⁵	1.3		1.3
Thermal Conductivity	ASTM C177	BTU•In/Hr•Ft ² •°F	1.75	W/m•K	0.25

Röchling Glastic Composites
 4321 Glenridge Road
 Cleveland, OH 44121 USA
 Tel: 216-486-0100
 Fax: 216-486-1091
www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® and Glastherm® are registered trademarks of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

©2007 Röchling Glastic Composites. All Rights Reserved. Printed in USA.